TECHNICAL DATA SHEET

PORCELAIN CRUCIBLES

JIPO porcelain meets the requirements of the ISO/TC 48 standards. Thanks to its composition of clay, quartz and feldspar, it has a high softening temperature, allowing unglazed items to be used at up to 1,350 °C and glazed items at up to 1,100 °C. Its crystal composition $3Al_2O_3 \cdot 2SiO_2$ gives JIPO porcelain high mechanical strength and low linear thermal expansion.

ORIGIN	CZECH REPUBLIC
MANUFACTURED TO	ISO 1772 DIN 12 904
HS CODE	69091100

Low form

Diameter	Height	Capacity	Model	Reference
20 mm	14 mm	2.5 ml	1/20	**202.2014**
30 mm	19 mm	5 ml	1/30	**202.3019**
35 mm	22 mm	10 ml	1/35	**202.3522**
40 mm	25 mm	17 ml	1/40	**202.4025**
45 mm	28 mm	21 ml	1/45	**202.4528**
50 mm	32 mm	34 ml	1/50	**202.5032**
60 mm	38 mm	62 ml	1/60	**202.6038**



Medium form

Diameter	Height	Capacity	Model	Reference
25 mm	20 mm	4.5 ml	2/25	**201.2520**
35 mm	28 mm	12 ml	2/35	**201.3528**
40 mm	32 mm	20 ml	2/40	**201.4032**
45 mm	36 mm	30 ml	2/45	**201.4536**
50 mm	40 mm	45 ml	2/50	**201.5040**
60 mm	48 mm	80 ml	2/60	**201.6048**
70 mm	56 mm	120 ml	2/70	**201.7056**



Tall form

Diameter	Height	Capacity	Model	Reference
30 mm	38 mm	15 ml	3/30	**200.3038**
35 mm	44 mm	26 ml	3/35	**200.3544**
40 mm	50 mm	35 ml	3/40	**200.4050**
45 mm	56 mm	50 ml	3/45	**200.4556**
50 mm	62 mm	72 ml	3/50	**200.5062**
60 mm	75 mm	130 ml	3/60	**200.6075**



Comercial Labor, S.A
Grases, 9
08004 Barcelona

Telephone 934246225
934266135
labor@comerciallabor.com